

Manufacturer of Military Spec., Corps of Engrs. Spec, Industrial, & Marine Coatings

TECHNICAL DATA SHEET

TT-E-527 LUSTERLESS, LOW VOC, ALKYD ENAMEL FINISH

<u>DESCRIPTION:</u> This lusterless enamel is a one component, air drying alkyd based coating intended primarily for use on primed wood and metal surfaces as an exterior or interior finish coat for military and other special equipment. It is lead and chromate free.

CONFORMANCE: This product conforms to TT-E-527 Revision D (the latest Revision).

TECHNICAL DATA

GENERIC TYPE: Medium oil alkyd

COLOR & FINISH: As per Fed-STD-595

Colors, Lusterless Finish

FLASH POINT (MIN): 81°F (27.2°C)

% VISCOSITY (PACKAGE): 75-150 SEC. # 4 FORD CUP

% SOLIDS BY WEIGHT: 65 % SOLIDS BY VOLUME: 50

RECOMMENDED DRY FILM THICKNESS (DFT): 1.5-2.0 Mils/Coat

THEORETICAL COVERAGE @ 2.0 MIL:

(50 MICRONS)DFT: Approx. 400 Sq. Ft./Gallon

DRYING TIME @ 75 OF:

A.) SET TO TOUCH, HOURS: 2
B.) DRY HARD, HOURS: 8
C.) FULL HARDNESS, HOURS: 72

VOLATILE ORGANIC COMPOUNDS (VOC): 3.5 lbs./gallon or 420 g/l

RECOMMENDED THINNER:

(FOR THINNING & CLEANING)
T-81772 Type III Alkyd Thinner

SHELF LIFE: 1 Year

SURFACE PREPARATION:

This product is designed to be applied over blasted or primed steel. Ensure that the surface is free from contaminants.

METHOD OF APPLICATION:

Can be applied by conventional spray, brush or a roller. Mix the product thoroughly before use. If required, thin up to a maximum of 5% of T-81772 Type III Alkyd Thinner.

Simco Coatings Inc.

211 Gunther Ln., Belle Chasse, Louisiana 70037 U.S.A.
Tel: (504) 393-9455 Fax: (504) 433-1406 Toll Free: 1-866-95SIMCO
e-mail: sales@simcocoatings.com web: www.simcocoatings.com

Manufacturer of Military Spec., Corps of Engrs. Spec, Industrial, & Marine Coatings

TT-E-527 LUSTERLESS, LOW VOC, ALKYD ENAMEL FINISH

SAFETY PRECAUTIONS:

- (A) Use normal precautions such as gloves and facemasks.
- (B) Adequate ventilation must be maintained.
- (C) Explosion proof lights and electrical equipment.
- (D) Non-sparking shoes and tools for workers in area.
- (E) This product contains flammable materials. Forbid all flames, smoking and welding in work area.
- (F) Avoid breathing of vapor, contact with skin and eyes. If product comes in contact with skin or eyes, wash thoroughly with water and obtain immediate medical attention.

NON-WARRANTY: The technical data listed herein has been compiled for your convenience and guidance, and is based upon our experience and knowledge. However, since we have no control over the use of this information or of this product, no warranty, expressed or implied, is intended or given. Simco Coatings, Inc. assumes no responsibility whatsoever for the coverage, performance or any other damages, including injuries resulting from the use of this information or of products recommended herein.

Simco Coatings Inc.

211 Gunther Ln., Belle Chasse, Louisiana 70037 U.S.A. Tel: (504) 393-9455 Fax: (504) 433-1406 Toll Free: 1-866-95SIMCO e-mail: sales@simcocoatings.com web: www.simcocoatings.com